UK Fixings (Southern) Ltd, Station Road, Sutton, nr Ely, Cambridgeshire CB6 2RL				
Tel. for Information: ++ 44 (0)1353 775 775 Fax for Information: ++44 (0)1353 777 007			3 777 007	
	Last Update 03.08.10	:	Status: Uncontrolled	Page 1 of 2

UKf HV Cyanoacrylate Adhesive

APPLICATIONS

Bonds metals, plastics, wood, ceramics, rubber, leather, card, glass and many other materials.

INSTRUCTIONS FOR USE

Clean and dry surfaces to be bonded. Apply adhesive sparingly to one surface and assemble parts. Hold or clamp parts together for 60 seconds.

USEFUL NOTES/HINTS

- General purpose
- Fast cure

CURED PERFORMANCE

Cured speed

•		
Aluminium	40-60 seconds	
Stainless steel	30-60 seconds	
Copper	10-20 seconds	
SBR	10-15 seconds	
Steel	10-30 seconds	
PVC	15-20 seconds	
Polycarbonate	10-40 seconds	

SHEAR STRENGTH

Grit blasted steel	>20 N/mm ²
Etched aluminium	>20 N/mm ²
Stainless Steel	>20 N/mm ²
Polycarbonate	>10 N/mm ²
Copper	>13 N/mm²
ABS	>5 N/mm ²

UK Fixings (Southern) Ltd, Station Road, Sutton, nr Ely, Cambridgeshire CB6 2RL				
Tel. for Information: ++ 44 (0)1353 775 775 Fax for Info			ormation: ++44 (0)1353 777 007	
	Last Update 03.08.10		Status: Uncontrolled	Page 2 of 2

LIQUID PROPERTIES

Ester base	Methyl
Appearance	Clear, colourless
Flash point	>81°C
Density	1,10
Shelf life	12 months unopened
Viscosity (brookfield)	1200 - 1800 cp
@	
25°C	

POLYMER PROPERTIES

Appearance	Clear, colourless
Softening point	c. 160°C
Refractive index	1,45
Full cure time	24 hours
Solubility	DMF, acetonitrile, acetone

STORAGE

UKf cyanoacrylates should ideally be stored in original sealed containers until used. Containers should be stored between 10°C and 22°C, avoid exposure to strong light and heat sources. Refrigeration can prolong shelf life.

PRESENTATION

UK Fixings (Southern) Ltd cyanoacrylate is available in 20g, 50g & 500g bottles as standard items.

PRECAUTIONS: This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheets (MSDS) for this and all other products being used are understood by all persons who will work with the product.

Warranty: All products purchased from or supplied by UK Fixings (Southern) Limited are subject to terms and conditions set out in the contract. UK Fixings (Southern) Limited warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by UK Fixings (Southern) Limited is consider accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. UK Fixings (Southern) Limited

makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will nor infringe any patent.