

## PRODUCT SPECIFICATION SILOXAMA11

### Product Description

SILOXAMA11 is a two component structural methacrylate adhesive, designed for the bonding of high strength metal and composite applications. It has been formulated from innovative technology, including our revolutionary adhesion system. This unique system enables the adhesive to achieve the ultimate balance of mechanical strength and impact resistance whilst still remaining both simple and quick to use.

### Typical Applications

SILOXAMA11 is very versatile and can bond a wide variety of substrates without the need for surface primers or conditioners. Typical examples are shown below:

- Bonding metal fasteners to moulded composite parts
- Bonding aluminium and stainless steel lettering in the sign manufacturing industry.
- Bonding automotive carbon fibre body panels
- Bonding GRP in the marine industry
- Bonding dissimilar metals for trailer fabrication

### Instructions For Use

1. Always consult MSDS before using this product for the first time.
2. Carry out surface preparation where required.
3. Remove cap, and attach mixer nozzle.
4. Dispense sufficient adhesive to ensure equal mix.
5. Apply adhesive to one surface and assemble components carefully, clamping if required.
6. It is always easier to remove any excess adhesive prior to cure using a suitable cleaner
7. Allow the adhesive sufficient time to achieve handling strength before moving or unclamping components.

### Properties of Uncured Material

Resin	Methyl Methacrylate
Colour	Yellow/White
Appearance	Thixotropic Gel
Viscosity Brookfield T Bar	120,000 to 150,000cps
Cure System	Exothermic
	7 Minutes@ 20°C
Handling Strength	12 Minutes@ 20°C

### Performance of Cured Material

ASTM D1002 Lapshear	Up to 30 Nmm <sup>2</sup>
ASTM D638 Tensile Strength	Up to 30 Nmm <sup>2</sup>
Gap Fill	4mm
Temperature Range	-55°C to 120°C

### Packaging

SILOXAMA11 is available in 50ml nylon cartridges for use with a dispensing gun.

SILOXAMA11 should be stored unopened in a cool, dry location out of direct sunlight. Stored correctly, this grade can offer a 12 month shelf life from manufacture.

### Health and Safety in Use

SILOXAMA11 is a methyl methacrylate and should not be used without consulting the MSDS, which contains full information regarding the use of this product, including Transport, Disposal, Toxicological, Exposure Controls, Accidental Release and First Aid measures essential to the safe use of this product.

**Disclaimer:** The data contained herein are furnished for informational purposes only and are believed to be reliable. However, Siloxa does not assume responsibility for any results obtained by persons over whose methods Siloxa has no control. It is the user's responsibility to determine the suitability of Siloxa's products or any production methods mentioned herein for a particular purpose, and to adopt such precautions as may be advisable for the protection of property and persons against any hazards that may be involved in the handling and use of any Siloxa's products. Siloxa specifically disclaims all warranties express or implied, including warranties of saleability and suitability for a particular purpose arising from sale or use of Siloxa's products. Siloxa further disclaims any liability for consequential or incremental damages of any kind including lost profits.