

## TECHNICAL DATA SHEET

**Technical data**

Basis	Polysiloxane
Consistency	Stable paste
Curing system	Moisture curing
Skin formation* (23°C/50% R.H.)	Approx 8 min
Curing speed * (23°C/50% R.H.)	Approx 2 mm/24h
Hardness**	Approx 23 ± 5 Shore A
Density**	Approx 1,00 g/ml (transp, brilliant white) Approx 1,22 g/ml (colours)
Elastic recovery (ISO 7389)**	> 80 %
Maximum allowed distortion	20 %
Max. tension (ISO 37)**	Approx 1,05 N/mm <sup>2</sup>
Elasticity modulus 100% (ISO 37)**	Approx 0,35 N/mm <sup>2</sup>
Elongation at break (ISO 37)**	Approx 600 %
Temperature resistance**	-60 °C → 120 °C
Application temperature	5 °C → 35 °C

\* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. \*\* This information relates to fully cured product.

**Product description**

Siloxa N is a high quality, elastic, 1-component sealant based on silicones.

**Properties**

- Very easy to apply
- Permanently elastic after curing
- Very good adhesion on many materials
- UV-resistant
- Very good resistance to ageing

**Applications**

- All usual building joints with high movement.
- Glazing and joint works.
- Expansion joints between many different construction materials.
- Sealing between PVC, treated wooden and metal profiles and glass.

**Packaging**

Colour: transparent, white, grey, black, brown, and many others

Packaging: 300 ml cartridge

**Shelf life**

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

## Substrates

Substrates: all usual building substrates Nature: rigid, clean, dry, free of dust and grease.

Surface preparation: Porous surfaces should be primed with a Primer. Prepare non- porous surfaces with a cleaner.

There is no adhesion on PE, PP, PTFE (Teflon®) and bituminous substrates. We recommend a preliminary adhesion and compatibility test on every surface.

## Joint dimensions

Min. width for joints: 5 mm Max. width for joints: 30 mm Min. depth for joints: 5 mm

Recommendation sealing jobs: joint width = 2 x joint depth. Three-point adhesion should be avoided at all time. Too small joint dimensions can have the effect that the silicone is pulled off because of too large movements.

**Remark:** This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. SILOXA reserves the right to modify products without prior notice.

## Application method

Application method: With manual- or pneumatic caulking gun.

Cleaning: Clean with White Spirit or Surface Cleaner immediately after use (before curing).

Finishing: With a soapy solution or Finishing Solution before skinning.

Repair: With the same material.

## Health and Safety Recommendations

Take the usual labour hygiene into account. Consult label and material safety data sheet for more information.

## Remarks

- Do not use on natural stones like marble, granite,...(staining).
- Direct contact with the secondary sealing of insulating glass units (insulation) and the PVB-film of safety glass must be avoided.
- Because of the diversity we recommend to do adhesion tests on aluminum lackers, textured coating and PVC before application.
- In an acid environment or in a dark room, a white sealant can slightly turn yellow. Under the influence of sunlight it will turn back to its initial colour.
- When finished with a finishing solution or soapy solution, make sure that the surfaces are not touched by this solution. This will cause the sealant not to adhere to that surface. Therefore we recommend to only dip the finishing tool in this solution.
- Do not use in applications where continuous water immersion is possible.
- Do not use on polycarbonate.
- When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.
- Contact with bitumen, tar or other plasticizer releasing materials such as EPDM, neoprene, butyl, etc. is to be avoided since it can give rise to discolouration and loss of adhesion.

## Environmental clauses

Leed regulation:

Siloxa N conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

Siloxa Building Chemicals, The Office, Three Pillars Business Park, Station Road, Sutton-in-the-Isle, Cambridgeshire CB6 2RU siloxa.co.uk

## **Liability**

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application

**Remark:** The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Siloxane reserves the right to modify products without prior notice