

## EVE TECHNICAL DATA SHEET

### CHARACTERISTICS

- Neutral 1-component silicone sealant
- Permanent elasticity
- Very easy to apply
- High resistance to high and low temperatures
- Excellent adhesion to almost all building materials
- High resistance to ageing and weather conditions

### APPLICATIONS

- Sealing of connection joints in building and construction.
- Forms a permanent water-tight and weatherproof bond to many surfaces such as glass, aluminium, etc.
- For use in sanitary applications: for seals in damp areas such as bathrooms, kitchens and cold rooms.

### TECHNICAL CHARACTERISTICS

TECHNICAL CHARACTERISTICS	
Type of product	Polysiloxanes
Density (g/ml)	1
Consistency	Pasta
Application temperature	+5°C - +40°C
Temperature resistance	-50°C - +150°C
Curing system	Curing by air humidity
Curing speed at 23 degrees C and 50% R.H. (mm, after 24h)	2.5 - 3
Skin forming time at 23°C and 50% R.H. (min.)	12
Shore A hardness: ISO 868	12
Elastic recovery capacity: ISO 7389	> 90%
Maximum permissible deformation: ISO 11600	20%
Modulus at 100% elongation: ISO 8339 (N/mm <sup>2</sup> )	0.32
% Elongation at break: ISO 8339	200
VOC	<100 g/l
Shelf life of unopened product	15 months
Storage conditions	Store in a dry, cool place at +5°C to +25°C. Keep out of direct sunlight.

### PACKING AND COLOURS

**25 x cartridge 300ML/box - 1200 pieces/pallet**

Transparent grey, Transparent

### METHOD OF USE

#### Preparation

- Use in well-ventilated rooms. Good ventilation is important during application and curing of the product.

Siloxa Building Chemicals, The Office, Three Pillars Business Park, Station Road, Sutton-in-the-Isle, Cambridgeshire CB6 2RU  
siloxa.co.uk

- The surfaces must be solid, dry and free of dust and grease.
- If needed degrease the materials to be glued with Parasilico Cleaner, MEK, fire alcohol, ethanol.
- The user needs to make sure that the product is suitable for the application. Consult our technical service if necessary.

## Primers

- Absorbent surfaces: Silicone Primer Porous Surfaces (transparent, drying time about 60 min.).
- Non-absorbent surfaces: Silicone Primer Non-Porous Surfaces (transparent, drying time about 60 min.).
- The use of a primer may be necessary on very porous substrates, in the event of difficulty in adhesion or in demanding conditions of use.

## Application

- Apply the product from the cartridge or foil packaging with a manual or pneumatic caulking gun.
- The size and shape of the joint is very important. Avoid thin joints.
- Do not subject the joint to thermal, mechanical or chemical stress before curing is complete.

## Tooling

- Smooth surface before skin formation with the Perfect Joint Tooling Agent and/or the Perfect Joint Tool.

## Cleaning

- Tools, surfaces and uncured residues can be removed with Parasilico Cleaner, Multi-Purpose Super Cleaner or Cleaning Wipes. Remainder of silicone can be removed with Silicone Remover after curing
- After curing remove mechanically.

## SAFETY

Consult the safety information on the packaging and the safety data sheet for more information.

## POINTS OF ATTENTION

- Not suitable for permanent submersion.
- Not suitable for use on butiminous surfaces.
- Not suitable for use on PE, PP, PA, PTFE (Teflon).
- Not suitable for use on polyacrylate and polycarbonate
- Not suitable for use on natural stone (can cause stains).
- Colours can yellow slightly in the absence of UV light or through contact with smoke or detergents.
- Not paintable.
- The sanitary formula is not a substitute for cleaning the joint. Heavy soiling and prolonged moist conditions can stimulate the development of fungi.
- Not suitable for glazing joints.
- Not suitable for contact with edge sealing of insulating glazing. Avoid direct contact.
- Not suitable for contact with PVB films of laminated glass. Avoid direct contact.

## TECHNICAL APPROVALS

- UKCA & CE according to EN 15651-1: F EXT-INT 20 LM
- UKCA & CE according to EN 15651-3: S XSI
- French VOC emission class A+
- Complies with FDA code 21 §177.2600 (e) (lanesco)