

## Soudaseal 215LM

Revision: 27/05/2020

Page 1 from 3

### Technical data

Basis	MS Polymer
Consistency	Stable paste
Curing system	Moisture curing
Skin formation* (23°C/50% R.H.)	Ca. 10 min
Curing speed * (23°C/50% R.H.)	Ca. 2 mm/24h
Hardness**	25 ± 5 Shore A
Density**	1,45 g/ml
Elastic recovery (ISO 7389)**	> 70 %
Maximum allowed distortion (ISO 11600)	± 25 %
Max. tension (ISO 37)**	1,30 N/mm <sup>2</sup>
Elasticity modulus 100% (ISO 37)**	0,36 N/mm <sup>2</sup>
Elongation at break (ISO 37)**	> 900 %
Temperature resistance**	-40 °C → 90 °C
Application temperature	5 °C → 35 °C
Water vapor diffusion resistance factor (μ)	1074
Water vapor permeability (Sd)	4,30 m

\* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. \*\* This information relates to fully cured product.

### Product description

Soudaseal 215LM is a high quality, neutral, elastic, 1-component joint sealant based on MS-Polymer.

### Properties

- Very low emission, EC1+ certified
- Good adhesion to most common substrates, even on slightly wet substrates
- Easy to tool, extrude (even at low temperatures) and finish in all weather conditions.
- Permanently elastic after curing
- No odour
- No bubble formation within sealant in high temperature and humidity applications.
- Primerless application on many substrates (except where water pressure may occur)
- No staining on porous surfaces such as marble, granite and other natural stones
- No hydrophobic effect on natural stone.
- Can be painted with water based systems
- Good weather and UV resistance
- Free of isocyanates, solvents, halogens and acids
- IFT certified

- RAL certified

### Applications

- Expansion and connection joints in the building industry: sealing of joints in prefabricated buildings, sealing between window and door frames,...
- Connection and expansion joints between window frames and walls.
- Expansion joints between many different construction materials.
- Sealing of expansion joints in facade systems with aluminum composite panels (see instructions of the supplier of the panels).
- Applications where the sealant needs to be overpainted with water based paints and varnishes.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

---

## Soudaseal 215LM

---

Revision: 27/05/2020

Page 2 from 3

**Packaging**

*Colour:* white, natural stone, dark beige, brown, concrete grey, grey, basalt grey, black, medium grey, brick red, dark brown, RAL7039 (quartz grey), RAL7016 (anthracite grey), other colors on request

*Packaging:* 290 ml cartridge, 600 ml foil bag, other packaging on request

**Shelf life**

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

**Chemical resistance**

Good resistance to water, aliphatic solvents, mineral oils, grease, diluted inorganic acids and alkalis. Poor resistance to aromatic solvents, concentrated acids and chlorinated hydrocarbons.

**Substrates**

*Substrates:* all usual building substrates, aluminium, stone, treated wood, PVC, ...

*Nature:* rigid, clean, free of dust and grease.

*Surface preparation:* Soudaseal 215LM has a good adhesion to most substrates. However, for optimal adhesion and in critical applications, such as joints exposed to extreme weather conditions, high- or water-loaded joints, we recommend to follow a pre-treatment procedure. Prepare non-porous surfaces with a Soudal activator or cleaner (see Technical Data Sheet). Porous surfaces should be primed with Primer 150.

Not suitable for PE, PP, PTFE (eg Teflon®), bituminous substrates, copper or copper-containing materials such as bronze and brass. We recommend a preliminary adhesion and compatibility test on every surface.

**Joint dimensions**

*Min. width for joints:* 5 mm

*Max. width for joints:* 30 mm

*Min. depth for joints:* 5 mm

Recommendation sealing jobs: joint width = 2 x joint depth.

**Application method**

Apply the product by means of a manual-, battery- or pneumatic- caulking gun. Apply Soudaseal 215LM evenly without air inclusions into the joint. Smoothen the joint with a spatula with the help of finishing solution. Avoid that soapy solution comes between the joint edges and sealant (to prevent adhesion loss).

*Application method:* With a manual, pneumatic or accu caulking gun.

*Cleaning:* Clean with Soudal Surface Cleaner or with Soudal Swipex, immediately after use

*Finishing:* With a soapy solution or Soudal Finishing Solution before skinning.

*Repair:* With the same material.

**Health- and Safety Recommendations**

Take the usual labour hygiene into account. Consult label and material safety data sheet for more information.

**Remarks**

- Soudaseal 215LM may be overpainted with water based paints, however due to the large number of paints and varnishes available we strongly suggest a compatibility test before application.
- Soudaseal 215LM can not be used as a glazing sealant.
- Soudaseal 215LM is non staining and suitable for sealing on natural stone on condition the joint dimensions and joint movement are respected. Avoid permanent pressure on the sealant.
- When applying, make sure not to spill any sealant on the surface of materials. Taping the surface around the joint can prevent this.
- A total absence of UV can cause a color change of the sealant.
- When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.
- Not suitable for bonding aquariums.
- Do not use in applications where continuous water immersion is possible.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

---

## Soudaseal 215LM

---

**Revision: 27/05/2020****Page 3 from 3**

- Discoloration due to chemicals, high temperatures, UV-radiation may occur. A change in color does not affect the technical properties of the product.
- Contact with bitumen, tar or other plasticizer releasing materials such as EPDM, neoprene, butyl, etc. is to be avoided since it can give rise to discolouration and loss of adhesion.

**Standards and certificates**

- Complies with ISO 11600 F 25 LM
- Belgium : ATG 98/2241 (ISO 11600-F-25LM)
- Meets ASTM C920 Type S, Grade NS, Class 50, Use T, NT, A and G
- Tested according to ASTM C1248: no staining on natural stone
- IFT certified according to QM360
- RAL certified according to RAL-GZ 711

**Environmental clauses***Leed regulation:*

Soudaseal 215LM conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

**Liability**

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.