



CHARACTERISTICS

- Acrylic emulsion based adhesive
- Solvent free and odourless
- No nails or screws needed
- Immediate adhesion
- Filling capacity
- Very high traction adhesive

APPLICATIONS

- Especially developed for assembling and sealing elements in polystyrene or expanded polyurethane
- Also suitable for bonding on concrete, masonry, plaster, wood, metal, PVCu, etc.

TECHNICAL CHARACTERISTICS	
Consistency	Paste
Base	Synthetically elastomere-emulsion
Traction resistance after drying	45 kg/cm ²
Colour	White
Density	1,65 kg/l
Open time	13 - 18 min.
VOC	< 50 g/l
Shelf life, in the original packing in dry conditions between +5°C - +25°C	Min. 12 months
Temperature resistance	-25°C - +70°C

PACKING AND COLOURS
25 cartridges of 310 ml/box - 48 boxes/pallet
White

Other colours are available on request (75 cartridges or multiples).

METHOD OF USE

Preparation

The surfaces must be clean, dry, sound and free of dust.

Application

- Apply in bands or plots.
- Bring together both surfaces in order to obtain good moistening.
- Separate the surfaces for 2 to 5 minutes and readjust the assembling. Press down firmly in the final position. The last readjustment can be changed during 30 minutes.
- Heavy materials exceeding 8 kg/m² must be supported for 8 to 15 hours.
- A good adhesion is obtained after 1 hour but wait at least 24 to 48 hours before submitting the supports to traction.

Cleaning

With water

SAFETY

Safety data sheet available on request.

TECHNICAL APPROVALS

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.



* Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).